



**Era Polymers Pty. Ltd.**  
25-27 Green Street, Banksmeadow  
Sydney, NSW 2019  
AUSTRALIA  
www.erapol.com.au

## Erapol E95A

POLYETHER (PTMEG) TDI PREPOLYMER

# TECHNICAL DATASHEET

**Erapol E95A** is a liquid isocyanate terminated pre-polymer based on PTMEG polyether polyol.

Polymers made from **Erapol E95A** exhibit outstanding abrasion, impact and chemical resistance, along with high load bearing capacity.

## Application

Typical uses of this polymer include sheeting, forklift truck tyres, rolls, and gears, die pads etc.

## Product Specification

<b>% NCO</b>	6.25 ± 0.25
<b>Specific Gravity @ 25°C</b>	1.07
<b>Viscosity @ 80°C (cps)</b>	300 - 700
<b>Colour</b>	Clear, light amber

## Mixing and Curing Conditions

		<b>E95A / MOCA</b>	<b>E95A / Ethacure 300</b>	<b>E95A / Eracure 110</b>
<b>Erapol E95A</b>	(pph)	100	100	100
<b>MOCA Level</b>	(pph)	19.0	-	-
<b>Ethacure 300 Level</b>	(pph)	-	15.0	-
<b>Eracure 110 Level</b>	(pph)	-	-	16.2
<b>Recommended % Theory</b>		95	95	95
<b>Erapol Temperature</b>	(°C)	75 - 85	65 - 75	65 - 75
<b>Curative Temperature</b>	(°C)	110 - 120	20 - 30	20 - 30
<b>Pot Life</b>	(mins)	6	4	5 - 6
<b>Demould Time @ 100°C</b>	(hrs)	1	1	1 - 2
<b>Post Cure Time @ 100°C</b>	(hrs)	16	16	16



This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.

## Physical Properties

Properties presented below are to be used as a guide and not intended for specification purposes.

		E95A / MOCA	E95A / E300*	E95A / E110**	TEST METHOD
<b>Hardness</b>	(Shore A)	95 ± 3	93	95 ± 3	AS1683.15
<b>Tensile Strength</b>	MPa (psi)	45.0 (6527)	42.7 (6193)	41.0 (5947)	AS1683.11
<b>100% Modulus</b>	MPa (psi)	13.1 (1900)	11.0 (1595)	12.6 (1827)	AS1683.11
<b>300% Modulus</b>	MPa (psi)	18.8 (2727)	15.2 (2205)	27.2 (3945)	AS1683.11
<b>Angle Tear Strength, Die C</b>	(kN/m)	90	110	110	AS1683.12
<b>Trouser Tear Strength</b>	(kN/m)	42	38	40	AS1683.12
<b>Elongation</b>	(%)	390	420	420	AS1683.11
<b>DIN Resilience</b>	(%)	48	46	47	DIN53512
<b>DIN Abrasion Resistance 10N</b>	(mm <sup>3</sup> )	70	68	38	AS1683.21
<b>DIN Abrasion Resistance 5N</b>	(mm <sup>3</sup> )	25	28	19	AS1683.21
<b>Compression Set / 22 hr @ 70°C</b>	(%)	35	38	38	AS1683.13
<b>Cured Specific Gravity</b>	(g/cm <sup>3</sup> )	1.13	1.13	1.13	AS1683.4

Please note \* Ethacure 300

\*\* Eracure 110

## Processing Procedure

- Erapol E95A** should be heated to 80 ± 5 and thoroughly degassed at 1 - 5 mm Hg of vacuum until excessive foaming stops.
- The curative should be added to **E95A**, the MOCA must first be melted at 110 - 120°C prior to mixing and Ethacure 300/Eracure 110 processed at room temperature. After adding the curative, mix thoroughly, being careful not to introduce air into the mixture.
- Pour mixed materials into moulds that have been preheated to 80 - 100°C and pre-coated with release agent.

## Adhesion

Adhesion of Erapol based elastomers to various substrates is at best marginal if a primer is not used. Please consult Era Polymers for specific recommendations to improve adhesion.

## Handling Precautions

**Erapol E95A** contains small amounts of free TDI. Therefore the product should be used in well-ventilated areas. Avoid breathing in vapours and protect skin and eyes from contact.

In case of skin contact, immediately remove excess, wash with soap and water. For eye contact, immediately flush with water for at least 15 minutes. Call a physician.

If nose, throat or lungs become irritated from breathing in vapours, remove exposed person to fresh air. Call a physician.