



**Era Polymers Pty. Ltd.**  
25-27 Green Street, Banksmeadow  
Sydney, NSW 2019  
AUSTRALIA  
www.erapol.com.au

## Erapol ET95A

POLYETHER (PTMEG) TDI PREPOLYMER

### TECHNICAL DATASHEET

**Erapol ET95A** is a liquid isocyanate terminated pre-polymer based on PTMEG polyether polyol. It has the advantage of being liquid at room temperature, low viscosity and fast cure.

Polymers made from **Erapol ET95A** exhibit outstanding abrasion, impact and chemical resistance as well as excellent dynamic properties.

#### Application

Typical used for this polymer include forklift truck tyres, rolls, gears etc.

#### Product Specification

<b>% NCO</b>	6.25 ± 0.25
<b>Specific Gravity @ 25°C</b>	1.06
<b>Viscosity @ 80°C (cps)</b>	300 - 700
<b>Colour</b>	Clear, light amber

#### Mixing and Curing Conditions

		ET95A / MOCA	ET95A / Ethacure 300
<b>Erapol ET95A</b>	(pph)	100	100
<b>MOCA Level</b>	(pph)	19.0	-
<b>Ethacure 300 Level</b>	(pph)	-	15.0
<b>Recommended % Theory</b>		95	95
<b>Erapol Temperature</b>	(°C)	75 - 85	65 - 75
<b>Curative Temperature</b>	(°C)	110 - 120	20 - 30
<b>Pot Life</b>	(mins)	4	2
<b>Demould Time @ 100°C</b>	(hrs)	< 1	< 1
<b>Post Cure Time @ 100°C</b>	(hrs)	16	16



This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.

## Physical Properties

Properties presented below are to be used as a guide and not intended for specification purposes.

		ET95A / MOCA	TEST METHOD
<b>Hardness</b>	(Shore A)	95 ± 3	AS1683.15
<b>Tensile Strength</b>	MPa (psi)	42.7 (6193)	AS1683.11
<b>100% Modulus</b>	MPa (psi)	6.9 (1001)	AS1683.11
<b>300% Modulus</b>	MPa (psi)	12.4 (1798)	AS1683.11
<b>Angle Tear Strength, Die C</b>	(kN/m)	85	AS1683.12
<b>Elongation</b>	(%)	380	AS1683.11
<b>DIN Resilience</b>	(%)	53	DIN53512
<b>DIN Abrasion Resistance 10N</b>	(mm <sup>3</sup> )	75	AS1683.21
<b>DIN Abrasion Resistance 5N</b>	(mm <sup>3</sup> )	26	AS1683.21
<b>Compression Set / 22 hr @ 70°C</b>	(%)	38	AS1683.13
<b>Cured Specific Gravity</b>	(g/cm <sup>3</sup> )	1.08	AS1683.4

## Processing Procedure

1. **Erapol ET95A** should be heated to the recommended processing temperature and thoroughly degassed at 1 - 5 mm Hg of vacuum until excessive foaming stops.
2. The curative should be added to **ET95A**, the MOCA must first be melted at 110 - 120°C and Ethacure 300 at 25°C prior to mixing. After adding the curative, mix thoroughly, being careful not to introduce air into the mixture.
3. Pour mixed materials into moulds that have been preheated to 80 - 100°C and pre-coated with release agent.

## Adhesion

Adhesion of Erapol based elastomers to various substrates is at best marginal if a primer is not used. Please consult Era Polymers for specific recommendations to improve adhesion.

## Handling Precautions

**Erapol ET95A** contains small amounts of free TDI. Therefore the product should be used in a well-ventilated area. Avoid breathing vapours and protect skin and eyes from contact.

In case of skin contact, immediately remove excess, wash with soap and water. For eye contact, immediately flush with water for at least 15 minutes. Call a physician.

If nose, throat or lungs become irritated from breathing in vapours, remove exposed person to fresh air. Call a physician.